

Artikel dapat dicermati selengkapnya pada web jurnal Chemistry Progress (http://ejournal.unsrat.ac.id/ index.php/chemprog/issue/ archive)

ISSN: 1979-5920

CHEMISTRY PROGRESS

Majalah Ilmiah Chemistry Progress merupakan media untuk menyebarkan informasi ilmiah dan sarana komunikasi bagi para ilmuan dan cendekiawan melalui tulisan-tulisan ilmiah. Majalah Ilmiah Chemistry Progress terbit pertama kali tahun 2008 dengan frekuensi dua nomor dalam satu tahun (Mei dan November) berisi kajian penelitian dalam lingkup ilmu kimia (organik, anorganik, analitik, biokimia, fisika, bahan alam, lingkungan, pangan, kelautan, pertambangan, farmasi dan komputasi).

Ketua Penyunting

Edi Suryanto

Wakil Ketua Penyunting

Frenly Wehantouw

Penyunting Pelaksana

Audy Wuntu Harry Koleangan Maureen Kumaunang Mariska Pitoi

Produksi dan Distribusi

Vanda S. Kamu

Percetakan

Sam Ratulangi Press, Manado

Isi diluar tanggungjawab percetakan

Alamat Redaksi :

JI. Kampus UNSRAT Kleak Manado, Sulawesi Utara. Kode Pos : 95115 Telp. (0431) 827964, 085256311981, Fax. (0431) 827964., Email: chemistryprogress@yahoo.com Website: http://ejournal.unsrat.ac.id/index.php/chemprog

PENERBIT

Jurusan Kimia, Fakultas Matematika Dan Ilmu Pengetahuan Alam, Universitas Sam Ratulangi Himpunan Kimia Indonesia Cabang Sulawesi Utara Screen Capture web yang memuat daftar isi makalah yang dimuat dalam vol. 7 no. 1 (<u>http://ejournal.unsrat.ac.id/index.php/chemprog/about/editorialTeam</u>)

CHEMISTRY PROGRESS

U SER. Username Password	HOME ABOUI LOG DI SEARCH CURRENI ARCHIVES WEBSIHE UNSKAJ WEBMALL UNSKAI PORIAL AKADEMIK PORIAL E-JOURNAL REPOSITORY UNSKAI
Esmember me	Home > Adout the Journal > Editorial Team
Log in	EDITORIAL TEAM
OURNAL CONTENT	
fearch.	PENANGGUNG JAWAB
All 💉	Prof. dr. Edwin de Queljoe, Universitas Sam Ratulangi, Indonesia
Browe	KETUA REDAKSI
By Issue By Anthon	Prof. Dr. Edi Suryanto, Universitas Sam Ratulangi, Indonesia
Other Journal:	SEKRETARIS
	Ir. Audy Wuntu, Universitas Sam Ratulangi, Indonesia Frenly Wehantouw, Universitas Sam Ratulangi, Indonesia
	BENDAHARA
	Johnly A. Rorong, Universitas Sam Ratulangi, Indonesia
	DEWAN REDAKSI
	Dra. Meiske Sangi, Universitas Sam Ratulangi, Indonesia
	Lidya Momuat, Universitas Sm Ratulangi, Indonesia Drs. Herling Tanghuman, Universitas San Ratulangi, Indonesia
	Dewa G. Katja, Universitas Sm Ratulangi, Indonesia
	Henry Aritonang, Universita: Sam Ratulangi, Indonesia
	Ir. Harry Koleangan, Universitas San Ratulangi, Indonesia
	Drs. Jemmy Abidjuhi, Universitas Sam Ratulangi, Indonesia Maureen Kumaunang, Universitas Sam Ratulangi, Indonesia

Screen Capture web yang memuat daftar isi makalah yang dimuat dalam vol. 7 no. 1 (http://ejournal.unsrat.ac.id/index.php/chemprog/issue/view/698/showToc)

VOL 7, NO 1 (2014)

TABLE OF CONTENTS

ARTICLES

Catalytic activity test of Mo-V-Te-Nb-Oxide in ammoxidation of	PDF
propane to acrylonitrile Restu Kartiko Widi	
Analisis kapasitas tukar kation birnessite	PDF
Pepi Helza Yanti	
Fotokatalis TiO2-zeolit untuk degradasi metilen biru	PDF
Nevi Dwi Andari	
Efisiensi dan karakterisasi komposit karboksimetil kitosan dan fraksi amilosa sebagai inhibitor korosi pada permukaan baja lunak dalam media HCl 1 M	PDF
Maria Erna	
Pembuatan tes kit kertas nitrogen-amonia berdasarkan pembentukan senyawa indiofenol biru	PDF
Hermin Sulistyarti	
Kajian Proses Produksi Garam Aneka Pangan Menggunakan Beberapa Sumber Bahan Baku	PDF
Eriawan Rismana	
Degradasi metilen blue menggunakan fotokatalis ZnO-zeolit	PDF
Eka Wahyu Putri Dini	
Korelasi fenolat total dan flavonoid total dengan antioksidan dari beberapa sediaan ekstrak buah tanjung (Mimusops elengi)	PDF
Charles Developed and	

Cahya Perwiratami

Screen Capture web yang memuat abstract article dalam (<u>http://ejournal.unsrat.ac.id/index.php/chemprog/article/view/4846</u>)

CHEMISTRY PROGRESS

USER Usemame Password Remember me Log In	HOME ABOUT LOG'IN SEARCH CURRENT ARCHIVES WEBSITE UNSRAT WEBMAIL UNSRAT PORTAL AKADEMIK PORTAL E-JOURNAL REPOSITORY UNSRAT Home > Vol 7, No 1 (2014) > Widi
JOURNAL CONTENT	
Search All Search Browse By Issue By Anthor By Title Other Journals	CATALYTIC ACTIVITY TEST OF MO-V-TE- NB-OXIDE IN AMMOXIDATION OF PROPANE TO ACRYLONITRILE Restu Kartiko Widi ABSTRACT
	The ammoxidation of propane has been investigated at a multicomponent oxidic, MoVTeNb catalyst in the temperature of 673 K. The catalyst was prepared by sol-gel method, and dried by spray dried method. The activity test of the catalyst has been carried out using micro reactor and showed that it was active for ammoxidation of propane to acrylonitrile.
	Keywords : ammoxidation, propane, mixed metal oxide catalyst, acryilonitrile

Screen Capture web yang memuat article dalam format PDF (<u>http://ejournal.unsrat.ac.id/index.php/chemprog/article/view/4846/4371</u>)

CHEMISTRY PROGRESS USER HOME ABOUT LOGIN SEARCH CURRENT ARCHIVES WEBSITE Usemane UNSRAT WEBMAIL UNSRAT PORTAL AKADEMIK PORTAL E-JOURNAL Password REPOSITORY UNSRAT Remember me Home > Vol 7, No 1 (2014) > Widi Log In — 🕂 Perbesaran Otomatis 🖨 3 Laman: 1 dari 4 4 JOURNAL CONTENT ~ Search All ¥ CATALYTIC ACTIVITY TEST OF Mo-V-Te-Nb-OXIDE IN AMMOXIDA TIO OF PROPANE TO ACRYLONITRILE Search Resta Kartile Widi Browse ¹ Department of Chemical Engineering University of Sarahasa By Issue By Author ABSTRAK By Title Other Journals Widt, R. K. 2014. Catalytic activity fast of No-V-To-Nb-Code in antimodation of proplam to actyle while This arrenzed aton or propone have been involvigated at a maliteringeneet exists, MeVTakia canded in the temperature of 873 K. This addyof was proposed by kelligal method, and drive by spray dried method. This address that the canded have finance control out using micro machine and intensid that it was active to arminosotiation of property to acylorately. Kata kundi rammoxidation, propana, mixed matal oxide catalyst, acrytoritria ABSTRACT Web, R. K. 20 M. UJ aktivias takalmistiko V. To No-Godu pada ammotadasa propana menjadi akelenini This ammostitution of programs from beam intensigned at a malicomposition oxetic, NM/Table calculate in this temporatory of 872 K. The calculate temporate by selligied matrices, and dread by spray dread matrices. This activates the basis cannot be basis cannot be using micro machine and discards from it was active to any micro machine to acciliate the basis cannot be basis. Keywords : ammostation, propane, mixed metal oxide catalyst, acryllorithie INTRODUCTION Selective exhiptic existention and ammetrikation ornik exhiptic using related by Uthilvies at processes of hydrocarbon comparis approximately (Mankrastal, 2000).

CATALYTIC ACTIVITY TEST OF Mo-V-Te-Nb-OXIDE IN AMMOXIDATION OF PROPANE TO ACRYLONITRILE

Restu Kartiko Widi¹

¹ Department of Chemical Engineering, University of Surabaya

ABSTRAK

Widi, R. K. 2014. Catalytic activity test of Mo-V-Te-Nb-Oxide in ammoxidation of propane to acrylonitrile

The ammoxidation of propane has been investigated at a multicomponent oxidic, MoVTeNb catalyst in the temperature of 673 K. The catalyst was prepared by sol-gel method, and dried by spray dried method. The activity test of the catalyst has been carried out using micro reactor and showed that it was active for ammoxidation of propane to acrylonitrile.

Kata kunci : ammoxidation, propane, mixed metal oxide catalyst, acryilonitrile

ABSTRACT

Widi, R. K. 2014. Uji aktivitas katalisis Mo-V-Te-Nb-Oxide pada ammoksidasi propana menjadi akrilonitril

The ammoxidation of propane has been investigated at a multicomponent oxidic, MoVTeNb catalyst in the temperature of 673 K. The catalyst was prepared by sol-gel method, and dried by spray dried method. The activity test of the catalyst has been carried out using micro reactor and showed that it was active for ammoxidation of propane to acrylonitrile.

Keywords : ammoxidation, propane, mixed metal oxide catalyst, acryilonitrile

INTRODUCTION

Selective catalytic oxidation and ammoxidation processes of hydrocarbons comprise approximately one quarter of the value produced by all catalytic processes world wide. They contribute hence significantly to the gross national product of industrial countries and affort future opportunities developing countries. These processes are not only important from a commercial standpint and their contribution to the well-being ofmodern mankind, but they also present the opportunity fo significant fundamental research. Such research ais at the molecular level understanding of catalytic behaviour, forming a basis for rational design of catalyst improvement of existing processes and the discovery of totally new catalysts and processes (Betahar et al., 1996).

The selective oxidation of lower alkanes to various functionalized molecules has attracted much interest in recent year. Propane partial oxidation to acrylic acid over vanadium pyrophosphate (VPO) catalysts has been reported. Propane oxidation to acrylic acid with heteropolyacids or with their corresponding salts has also been reported. In propane ammoxidation to acrylonitrile, V-Sb oxide catalysts were studied by several researchers and Mo-V-Te-Nboxide catalysts were studied by Ushikubo at al. (Manhua et al., 2000).

This paper limits itself to the activity test of diluted Mo-V-Te-Nb-oxide catalyst for propane ammoxidation processes.

MATERIALS AND METHODS

Catalyst preparation

Preparation of solution 1 (Mo-V-Te)

Eleven point two and seven grams of AHM was dissolved in 100 ml of water. This solution was heated up to 353 K. A clear solution was obtained from AHM. This solution was stirred at a speed of 700 rpm. After complete dissolution of the solid, 2.24 g of AMV was added, and 3.37 g of Telluric acid was added after the AMV had dissolved completely.

Preparation of solution 2 (Nb)

Three point five and four grams of Niobium ammonium oxalate was dissolved in 29 ml of water. This solution was stirred until all solids had dissolved without heating. Solution 1 was heated up to a

Activation

The dried material was precalcined from room temperature to 598 K at a rate of 10 K/min in air (100 ml/min) for 1 h and then calcined from room temperature to 923 K at a rate of 2 K/min in helium (100 ml/min) for 2 h.

Catalytic activity test

Approximately 10 g of catalyst was packed in an 12 mm ID stainless steel tubular reactor and tested at 673 K at a propane/O₂/He/NH₃ mole ratio of 1/3/18/3, a space velocity of 1200 h⁻¹ and a pressure of 1 atm. The product streams were analyzed by gas chromatography (GC) by means Agilent.

RESULT AND DISCUSSION

Acrylonitrile (ACN) is an important intermediates in petrochemistry and exhibit excellent annual growth; the main application includes synthetic fibers and resins. For decades, the ammoxidation of proplylene to acrylonitrile is the most important process whereby more than 5 billion kg/year of acrylonitrile (with growth rate of 4% per year) are produced worldwide via the SOHIO/BP process. The said process is very efficient, fully converting propylene at the same time giving > 80% acrylonitrile yield on commercial scale.

The chemical equation of the SOHIO/BP process as extracted from literature (Olga et al., 2004) is given as follow:-

$$C_3H_6+NH_3+3/2O_2 \rightarrow CH_2=CH-CN+3H_2O$$

Catalyst: $(K,CS)_{0.1-0.2}$, Ni,Co,Mn,Mg)_{7.5-9.5}, $(Fe,Cr)_{2.3-2.5}$, Bi_{0.5-1.0}, Mo₁₂O_x/SiO₂ (MCM)

Despite the efficiency of the process, the price of propylene has seen attention being drawn to develop a method for producing acrylonitrile by ammoxidation reaction whereby lower alkane such as propane is used as a starting material *i.e.* propane catalytically reacted with ammonia and oxygen in a gaseous phase in the presence of a catalyst. Beside the economical factor of propane being a cheaper and more abundant feed, ammoxidation of propane is also a less energy intensive process. As such, promising acrylonitrile yield above 58% have already been obtained from propane using a patented Mo-V-Nb-Te-O_x catalyst developed by Mistsubishi Chemical Company (Olga et al., 2004).

Future Process utilizing propane as starting material:-

$$C_3H_8+NH_3+2O_2 \longrightarrow CH_2=CH-CN + 4 H_2O$$

Mo-V-Te-Nb mixed oxides is an interesting developing catalyst in the transformation of shortchain alkanes, *i.e.* C1-C4. It has been known that acrylonitrile (ACN) and acrylic acid (AA) can *selectively* be obtained in the ammoxidation and the oxidation of propane. Observation made based on the previous work of Olga et al. (2004) found that the best catalysts (V-Sb-Al) for ammoxidation are those exhibited the lowest yield in the oxidation process to acrylic acid and vice versa. The fact that Mo-V-Te-Nb-oxides could be used in both ammoxidation and/or oxidation underlines the advantage of this new multimixed oxide catalyst as compared to conventional catalysts such as Sb-containing material (V-Sb-Al, Mo-V-Sb-Ox, etc.) (Hinago & Komada, 2000).

The formation of acrylonitrile (ACN) also strongly depends on the presence of ammonia. The proportion of ammonia to be supplied for the reaction is preferably within a range of from 0.2 to 5 moles, particularly from 0.5-3 moles, per mol of propane (Ushikubo, 1995)



Figure 1. The schematic diagram of the reactor for ammoxidation of propane

In the absence of ammonia, only acrylic acid is obtained over Mo-V-Te-Nb catalyst [5]. The incorporation of ammonia using the same catalyst increases both the propane conversion and the selectivity to ACN although the catalytic results depend strongly on the NH_3 / C_3H_8 ratio. Therefore, *caution* need to be taken to juggle the proportion of feeds used, i.e. propane/oxygen (air)/ ammonia. In too excess of oxygen, higher conversion of propane as a

trade off to the selectivity of nitriles may be obtained. On the other hand, the use of the right NH_3/C_3H_8 ratios may be in favors to an important decrease in propane conversion and at the same time increase in the selectivity to ACN.

The activity test of Mo-V-Te-Nb-oxide catalyst from this study using the reactor (figure 1) is shown below (figure 2);



Figure 2. Catalytic Performance for Propane Ammoxidation Using Petrochemical Reactor

Figure 2 describes that the Mo-V-Te-Nb-oxide catalyst used for this reaction is active for ammoxidation of propane to acrylonitrile. The conversion of propane is about 18% and the selectivity to acylonitrile is slightly increased from about 42% to 47% during the reaction. This indicates that the catalyst is active until 12 hours reaction. It might be still active even if the reaction is carried out for longer time. The potential of this catalyst for propane ammoxidation need to improve, since the product stream still contains COx (CO2 and CO) in quite high amount. There are some suggestions to improve the catalytic performance of this catalyst, i.e. improve the drying process, improve the calcinations process, or improve the reaction condition of propane ammoxidation.

CONCLUSIONS

Based on the result, it can be concluded that Mo-V-Te-Nb-oxide catalyst is an active catalyst for ammoxidation of propane to acryilonitrile. The formation of acrylonitrile (ACN) strongly depends on the presence of ammonia..

ACKNOWLEDGMENT

This research has been carried out in the COMBICAT Laboratory, University of Malaya Kuala Lumpur, Malaysia.

REFERENCES

- Betahar, M. M., Costentin, G., Savary, L. & J.C. Lavalley. 1996. On the partial oxidation of propane and propylene on mixed metal oxide catalysts. Applied Catalyst A: General 145, p. 1-48
- Hinago, H. & S. Komada. 2000. Ammoxidation catalyst for use in producing acrylonitrile or methacrylonitrile from propane or isobutane by ammoxidation, US Patent 6,063,728.
- Manhua, L., Tejal, B., Desi., Frederick, W., Kaiser & P. D. Klugherz. 2000. Reaction pathways in the selective oxidation of propane over a mixed metal oxide catalyst *Catalyst Today* 61 (1-4), p 223-229
- Olga, M. G. P., Jamal, N. A., Vadim V. G. & A. B. Miguel. 2004. Catalytic properties of mixed Mo-V-Sb-Nb-O oxides catalysts for the ammoxidation of propane to acrylonitrile, Applied Catalysis A: General 260 (1), p.93-99
- Ushikubo, T., Oshima, K., Kayo, A., Umezawa, T., Kiyono, K., Sawaki, I. & H. Nakamura. 1995. Catalyst for the production of nitriles, US Patent 5,472,925.